EZ LINER BEDLINER & INDUSTRIAL STRENGTH COATING

TECHNICAL DATA SHEET

Stock	Product	Colour	Size
BEZLG / 100105	EZ Liner Bed Liner & Industrial Strength Coating (2 part kit)	Black	3.78L / 1 U.S. gal

DESCRIPTION:

EZ Liner is a revolutionary coating, with excellent adhesion to most surfaces including truck beds, metals, plastics, wood, fiberglass and concrete. Excellent for basement and garage floors, steps and pool decks.

FEATURES:

- Very low VOC.
- Easily applied by brush, roller or Dominion Sure Seal's BUPA gun.
- Low odour.
- Extremely chemical resistant.
- Seals out moisture & corrosion.
- Incredible wear & tear resistance.
- Excellent anti-skid coating.

SURFACE PREPARATION:

1. Surface to be coated must be cleaned with a good quality wax and grease remover.
2. Loose paint / rust should be removed and affected areas primed.
3. Sand area with 120 grit sandpaper. Blow off and re-clean. Surface should be clean and dust free.
4. Mask all areas surrounding application area. Additional masking may be required depending on experience.

APPLICATON:

1. Gradually pour contents of Part B Polymer Resin into the gallon can of Part A Black Base material while mixing.

2. Add a maximum of 24 drops of Part C accelerator per 1 gallon of EZ Liner. (The Part C Accelerator dropper bottle contains more. By using more, pot/work time will be reduced.) See chart for times.

3. Mix vigorously by hand for 5 minutes using a paint mixing stick. ***Do not thin with any additional solvents***.

4. Apply immediately after mixing. See Steps Below.

If Brushing:

1. Apply with a natural or synthetic brush (included in kit), in even strokes until sufficient coverage is achieved.

If Rolling:

1. Apply with the roller included in the kit. Apply even strokes until desired finish is achieved.

If Spraying:

2. Pour mixed contents into Schutz can provided and attach Dominion Sure Seal's Schutz Gun (BUPA). Set air pressure at the Schutz Gun between 40-60 psi and spray one even coat until coverage is uniform. Wear an approved respirator during spray operations. A second light coat may be applied after 30-60 minute flash time.

FOR PART C ACCELERATOR:

Drops	Work Time	Tack Free
0	Over 1 hour	8 - 9 Hours
12	Over 1 hour	6 - 7 Hours
24	50 minutes	4 - 5 Hours

TECHNICAL PROPERTIES:

Practical Coverage:	100-120 sq. ft. per 1 gal kit @10-12 mils wet
Optimum Film Thickness:	10-12 mils wet film per coat
Recommended Number of Coats:	1-2
Flash Time:	30-60 minutes between coats*
Ready for Light Duty:	2 Days*
Full Cure, Ready for Regular Duty:	3-7 Days*

*Times stated are at 72° F (22° C). Cure times will be extended if applied under cooler, low humidity conditions, if less Part C Accelerator is used or if a higher wet film build is applied. ***Do not apply this product near catalytic converters & mufflers due to extreme heat.***

EZ LINER BEDLINER & INDUSTRIAL STRENGTH COATING

TECHNICAL DATA SHEET

CLEANING:

Clean tools immediately after use with lacquer thinner. Cured product can only be removed mechanically.

PERSONAL PROTECTION:

Contains Products that may be harmful if misused. Read instructions on individual containers carefully. Keep out of reach of children. All users should review the Safety Data Sheet (SDS) prior to use for possible health hazards. Copies of the SDS sheet are available upon request.