

# EZ Liner Bedliner aerosol TECHNICAL DATA SHEET



---

Stock	Product	Colour	Size
SEZL / 24040	EZ Liner Bedliner and Industrial Strength Coating	Black	467g / 16.5 oz aerosol

## DESCRIPTION:

EZ Liner (SEZL) is specially designed to touch up tears, scratches and chips in existing bed liner coatings. EZ Liner is easy to apply and provides a durable and highly abrasion resistant coating that will rejuvenate most surfaces.

## FEATURES:

- Ready to spray, Fast drying
- Remains permanently flexible
- Seals out moisture and corrosion
- Abrasion and chemical resistant
- Anti-skid coating
- Great for touching up tear, scratches and chips in liquid bed liners

## DIRECTIONS FOR USE

### SURFACE PREPARATION:

1. Pre-clean area to be treated with soap and water, rinse thoroughly and dry. Remove all loose paint and rust with a wire brush. Treat / repair any rusted areas. Prime bare metal areas.
2. Clean surface area thoroughly with Panel Prep (SPPV) or Sure Solv (SUS), wipe clean and allow to dry. Lightly scuff / sand any bare metal or sound painted areas. Re-clean and dry.
3. Mask off any surrounding areas not to be coated.
4. For maximum adhesion apply adhesion promoter (SXPP24 or XPPPQ) after surface preparation is complete. Allow to dry 20 – 30 minutes before top coating.

### APPLICATION:

1. Agitate can thoroughly by inverting can and returning upright. Continue to agitate for at least 1 -2 minutes after mixing ball moves freely. Occasionally re-mix during use.
2. Spray steady, even coats with can about 6 to 12 inches from the surface.
3. Spray 2 medium wet coats until full coverage. Allow a 10 minute flash time between coats.
4. When finished, turn can upside down and spray about 2-3 seconds to clean out valve.

# EZ Liner Bedliner aerosol TECHNICAL DATA SHEET



## TYPICAL PROPERTIES:

Color	Black
Spray Pattern	Mist spray
Flash Time	10 minutes [1]
Touch Dry	10 - 15 minutes [1]
Full Cure	4 - 8 hours [1]
Product-Weighted Reactivity (PWR)	0.94 – 0.98 g O <sub>3</sub> / g product [2]
Product-Weighted MIR (PWMIR)	0.88 – 0.92 g O <sub>3</sub> / g product [3]
VOC Content, less exempt solvents	63 – 65 % w/w (<540 g/l)
Packaging	467 g (16.5 oz)

[1] Times stated are at 72°F (22°C). Times may vary depending on film build, temperature and air flow.

[2] Category: Non-Flat Coatings; 1.40 limit applies under US EPA.

[3] Category: Flexible Coatings; 1.60 limit applies in CA.

## STORAGE STABILITY:

Contents under pressure. Do not place in hot water or near radiators, stoves, or other sources of heat. Do not puncture or incinerate container or store at temperatures over 50°C. Store in a well-ventilated area away from heat, sparks or flames. The packaging must be protected from direct sunlight and heat. Store in a cool, well-ventilated environment.

## SAFETY PRECAUTIONS:

Contains acetone, methyl ethyl ketone, toluene, isobutyl acetate and dimethyl ether. **DANGER:** Extremely flammable. Contents under pressure. Harmful if inhaled. Use under well-ventilated conditions away from heat, sparks or flames. Avoid eye contact and prolonged contact with the skin. In case of eye contact, flush thoroughly with water for 15 minutes and get medical attention if irritation persists. If swallowed, seek medical advice immediately and show this container label. **KEEP OUT OF REACH OF CHILDREN.** For more information, please see our latest safety data sheet.

All figures, recommendations and safety precautions are based on thorough investigations and our actual experience and are without engagement. Although the documentation has been set up with most carefulness, we do not accept any responsibility for mistakes, inaccuracies or printer's errors. We reserve the right to adjust the product, whenever we feel necessary. Because the design, the quality of the substrate and the conditions during application fall beyond our control, no responsibility for executed works can be accepted on the basis of this documentation. We therefore recommend to carry out own tests on the spot. All our deliveries are subject to the General Terms and Conditions of Sale and Purchase of Dominion Sure Seal Ltd.

Dominion Sure Seal Ltd. | 6175 Danville Rd, Mississauga, ON. L5T 2H7

1 800 265 0790 | [www.dominionsureseal.com](http://www.dominionsureseal.com) Rev Feb 2019