


PRODUCT FEATURES & APPLICATION



Touch Dry 30min – 1hr

Dominion Sure Seal Ltd.

6175 Danville Road, Mississauga, Ontario, Canada L5T 2H7

TEL (905) 670-5411

FAX (905) 670-5174

OEM RUBBERIZED UNDERCOAT (SUPER PROTECTOR)

Stock BUR, Part # 1008 (Bulk)

Colour: Black

Description:

An easy to use Hi Build rubberized, (schutz gun applied) rubber undercoating and rocker panel coating that provides excellent abrasion and chip protection, sound deadening, and corrosion resistance.

Features:

- Easily applied direct from the aerosol can or bulk
- Hi build-up and texture
- Superior rubber content
- No odor when dry
- Quick drying

Surface Preparation

- Remove all loose paint, rust and dirt from areas to be undercoated with wire brush. Repair rust
- Clean the area to be sprayed with DSS Sure Solv Stock BSS Part 10058 or a high quality wax, and silicone remover.
- Rusted metal should be repaired and treated with DSS Rust remover Stock BRO Part 10044 (available in gel or liquid form)
- Lightly scuff bare metal areas that are to be treated.

Touch Dry and Paintable 30min – 1hour

Full Cure 4 – 24 hours

Application Instructions:

- Shake can vigorously, at least three minute. Shake aerosol until mixing ball breaks free.
- If application is in a tight area or if over-spray is a concern use an extension tube
- Hold can so nozzle is 12 to 16 inches from surface
- Application by schutz type gun: Keep gun 18 to 24 inches from area being sprayed and pressure at 50 psi.
- Application by Aerosol: Keep can about 18 to 24 inches from area being sprayed using even flowing motions.
- Apply 2 or 3 even coats for full coverage
- Apply by moving steadily and evenly
- Allow each coat to flash off for 5 minutes between coats
- Over-spray can be cleaned up with DSS BSS Part 10058 solvent.
- Allow Rubberized Undercoating to dry for a minimum 30 minutes at (70° F) before painting.

Note: Avoid applying any materials on or near catalytic converters, mufflers due to extreme heat.

In the event the MSDS (Material Safety Data Sheet) on this product is not in your files, you can request one from Dominion Sure Seal Regulatory Compliance at 1800 265-0790, ext. MSDS.

Call 1-800-265-0790 or visit us on the web www.dominionsureseal.com

BUR_2_2002